



HOUILLÈRES de CRUÉJOULS

# Mode d'emploi

DATE EDITED: 27/10/2009

DATE UPDATED: 30/11/2010

VERSION: 03

## Enduit fin

### AREAS OF USE

Adhesion-promoting or decorative renderings.  
Outside and inside.

### CHARACTERISTICS

Salubrious, natural, breathable, easy to apply thin lime render.

**Enduit fin à la chaux n°1:** fine particle size (about 0.6 mm).

**Enduit fin à la chaux n°2:** medium particle size (about 0.8 mm).

### COMPOSITION

Aerated lime, sand, marble powder.  
Adjuvants: 1%.

### SHADES

White. It is also possible to create shades using our pigments.

### EQUIPMENT

Plastering trowel, spatula, mechanical mixer.

### SURFACES

Ideally, the surface must be dry, open (porous) and non-chalking.

**Enduit fin à la chaux** cannot be applied to walls subject to rising damp.

■ **On standard surfaces** (plasterboard, plaster, cement rendering, concrete, old paint, etc.): apply our **Sous-couche acrylique granitée** (Granite-finish acrylic primer) to ensure adhesion. It is essential to apply two coats of our **Sous-couche acrylique granitée** to surfaces having differences in porosity due to sealing strips for example or to filler material.

Apply **Enduit fin à la chaux** when the primer is fully dry.

■ **On breathable surfaces** (lime render, earth render, etc.): wet the surfaces then apply **Enduit fin à la chaux** directly.

On jointed Fermacell board apply 2 coats of our **Sous-couche acrylique granitée**. On glued Fermacell, directly apply our **Enduit fin à la chaux n°1**.

■ **Outside: Enduit fin à la chaux** is applied as a finishing coat. (last coat of a three-coat outside render) before lime washing  
Preferably for an outside render, our **Enduit NHL** should be used.

### PREPARATION

Add 2 litres of water per 5 kg of **Enduit fin à la chaux**.

Mix 5 minutes with a mechanical mixer.  
Leave to stand.

To create new shades with our pigments, a deep hue is obtained with about 100 g of pigment per kg of dry **Enduit fin à la chaux**. Over and above this concentration a phenomenon of chalking may occur.

Some pigments (oxides and some mixtures) may leave traces of brighter colour (streaks). To reduce this risk, it is advisable to prepare a pigment paste.

To form this pigment paste, the entirety of the pigment or pigments must be mixed with part of the mixing water and a few drops of wetting agent. The more this paste is worked in before being mixed with **Enduit Fin à la chaux**, the lesser the risk of streaking.

### APPLICATION

It is advisable to carry out tests before applying to a large surface area.

Room temperature: 10°C to 30°C.

Apply with a plastering trowel or spatula in a thin coating about 2 mm thick for **Enduit fin à la chaux n°1** and up to 5 mm thick with **Enduit fin à la chaux n°2**.

DÉFI - HOUILLÈRES DE CRUÉJOULS  
ZI La Gloriette - 38160 Chatte - France

Tél. 33 (0)4 76 64 85 64 - Fax 33 (0)4 76 64 85 69 - Email [defi.h2c@orange.fr](mailto:defi.h2c@orange.fr)

Siret 331 014 993 000 58 RCS Grenoble - Code APE 4669B - N° TVA FR22331014993 - SAS au capital de 912 356 euros



HOUILLÈRES de CRUÉJOULS

### FINISHED APPEARANCE

Smooth, granite-finish or textured.

A stucco or lime wash can be applied to our thin lime render, after drying.

### YIELD

- Approximately 1.3 kg per m<sup>2</sup> (4 m<sup>2</sup> with 5 kg of **Enduit fin à la chaux n°1**).
- Approximately 2,5 kg per m<sup>2</sup> (2 m<sup>2</sup> with 5 kg of **Enduit fin à la chaux n°2**).

### DILUTION AND CLEANING

With water.

### PRECAUTION FOR USE

Work in a ventilated area and wear a dust mask to avoid any irritation due to the presence of lime. Refer to cautionary advice on the label.

### STORAGE

Store in a cool, dry place in the original, closed packaging.

Can be stored several months after use if the product is covered with water and the lid closed.

### IMPORTANT

The indications given are based on our state of knowledge of the products concerned and do not under any circumstance entail the providing of any guarantee. It is for users to carry out tests prior to use and to take the necessary safety precautions.

DÉFI - HOUILLÈRES DE CRUÉJOULS  
ZI La Gloriette - 38160 Chatte - France

Tél. 33 (0)4 76 64 85 64 - Fax 33 (0)4 76 64 85 69 - Email [defi.h2c@orange.fr](mailto:defi.h2c@orange.fr)

Siret 331 014 993 000 58 RCS Grenoble - Code APE 4669B - N° TVA FR22331014993 - SAS au capital de 912 356 euros